

PRODUCT CHART



Category	Grade	Density (g/cc)	MFI	Features	Typical Applications
Standard Grades	PolyLink PL4338	0.938	3.2	Broad Processing Latitude, Good ESCR	Storage Containers
	PolyLink PL4438	0.938	4	Good Impact strength	Pallets, Industrial bins, Water Tanks, Chemical Tanks
	PolyLink PL4536	0.936	5	Broad processing window, Good Impact Strength	General Moulding, Toys and Playground Equipment, Outdoor Storage Containers
	PolyLink PL4632	0.932	6	Easy to process	Mussel Floats or Buoys, Leisure Products, Agricultural Products, Truck Mudguards, Display Stands
	PolyLink PL4734	0.934	7	Easy to process in complex moulds	General Moulding
High Performance Grades	PolyLink PL6338	0.938	3.2	Good Mouldability, Hexene Grade	Storage Containers, Medium to Large Water Tanks, Chemical Tanks
	PolyLink PL6338UV	0.938	3.2	Hexene Grade, UV20 Rating	Storage Containers, Medium to Large Water tanks, Chemical Tanks
	PolyLink PL6438	0.938	4	Excellent Stiffness, Good Impact Strength, Hexene Grade	Toys and Playground Equipment, Medium to Large Water Tanks, Chemical Tanks
	PolyLink PL6534	0.934	5	Good Mechanical and Chemical Properties, Hexene Grade	Chemical Tanks, Storage Containers, General UV stabilised applications
	PolyLink PL8435	0.935	4	Octene Grade, Excellent ESCR	IBCs, Chemical Drums, Boats, Freezer Containers, Fish Crates, Small Tanks
Specialty Grades	PolyLink FT836BK	0.938	3.2	Good Mouldability, UV20 Rating, TUV Approved	Fuel Tanks
	PolyLink FT836BK-ER	0.938	3.2	Good Mouldability, UV20 rating, TUV Approved, Enhanced Release	Fuel Tanks
	PolyLink XL828	0.95	N/A	Crosslinkable PE, Exceptional Strength, Chemical Resistance	Fuel Tanks
	PolyLink PL4734FR-H	>1.000	7	UL-94 – V0, Flame Retardant	Flame Retardant Applications

Version 01/04-2020